

Ferro Silicon (FeSi) Specification

Type	Chemical					
	<u>Si</u>	<u>Al</u>	<u>P</u>	<u>S</u>	<u>C</u>	<u>Size</u>
FeSi 72 Al 2	Min 72%	1.4-2.0%	0.05% Max	Max 0.04%	Max 0.2%	10-60 mm (Min 90%)
FeSi 70 Al 2	Min 70%	1.4-2.0%	0.05% Max	Max 0.04%	Max 0.2%	10-60 mm (Min 90%)
FeSi 70 Al 2	Min 70%	1.4-2.0%	0.05% Max	Max 0.04%	Max 0.2%	3-10 mm (Min 90%)
FeSi 69 Al 2	Min 69%	1.4-2.0%	0.05% Max	Max 0.04%	Max 0.2%	0-3 mm (Min 90%)
FeSi 68 Al 2	Min 68%	1.4-2.6%	0.05% Max	Max 0.04%	Max 0.2%	0-3 mm (Min 90%)
FeSi 67 Al 2	Min 67%	1.4-2.6%	0.05% Max	Max 0.04%	Max 0.2%	0-3 mm (Min 90%)

Reference standard: ISO 5445:1980, ISO 9001:2015, ISO 14001:2015

Packing: 1MT Bag