

### Grinding Ball Specification

Grade	Chemical										
	%C	%Cr	%Mn	%Si	%P	%S	%Cu	%Ni	%Mo	%Sn	%Al
70Cr2	0.65-0.75	0.55-0.70	0.75-0.90	0.2-0.3	≤0.03	≤0.03	≤0.30	≤0.4	≤0.1	≤0.06	≤0.1

### Grinding Ball Physical Properties

Standard	Material	Size	Volumetric Hardness	Surface Hardness
70Cr2	70Cr2	20 – 150 mm	58 – 65 HRC	55 - 65 HRC

Packing: Jumbo Bag (1000 kg) / Drum (850 – 950 kg)